



## VFI-200 POLYUREA SPRAY ELASTOMER SYSTEM

### Overview

■ **Description**

VFI-200 is a high performance, 100% solids, spray applied, aromatic pure polyurea elasto-plastic polymer. It is characterized by optimal physical properties, outstanding chemical and solvent resistance, and usability under wide climatic conditions with outstanding durability. It is composed of Isocyanate pre-polymers, which are reacted with amine pre-polymers to form a pure polyurea elasto-plastic polymer.

Both components are low viscosity fluids, which react very quickly to form a tough polymer when mixed and applied using heated, plural component airless spray equipment.

■ **Usage**

VFI-200 is primarily used for high abrasion and chemical resistant lining applications. Please contact Volatile Free, Inc. for application specifications:

■ **Color**

Standard color is black. This is an Aromatic product. Custom colors are available but may change with UV exposure.

### Physical Properties

■ **Hardness**

ASTM D-2240	
Shore A	94 ± 2
Shore D	50 ± 2

■ **Tensile Properties**

ASTM D-412	
Strength	2523 psi
Elongation	349%
Elastic Modulus	8244 psi
Yield Strength	1030 psi
Permanent Set	35% max

■ **Tear Strength**

ASTM D-624 Die C 425 ± 20 pli

■ **Solid Material Density**

66 pcf

■ **Cold Temperature Flexibility**

ASTM D-2240  
 Pass 0.25 inch Mandrel Bend Test at -40°F.

■ **Adhesion**

ASTM D-4541  
 Prepared & primed concrete >725 lbs/in<sup>2</sup> with concrete failure

### Weather & Environmental Performance

■ **Weatherability QUV Test Data**

ASTM G-53  
 No cracking, checking or loss of integrity after 2000 hours. This is an Aromatic product. Light colors yellow when exposed to UV light.

■ **Chemical Resistance**

Contact VFI for with specific chemicals for verification.

■ **Service Temperature**

-40°F to 180°F

■ **Hydrolytic Properties**

■ <b>Water absorption</b>	
ASTM D-471	1.5%
■ <b>Water Vapor Permeability</b>	
0% R.H. @ 73°F 45 mil film:	0.69 perms

■ **Fire Resistance**

Not rated

### Liquid Component Properties

■ **Ratio**

Volume 1 to 1

■ **Coverage**

mil/ft/gal 1600

■ **Solids**

100%

■ **Viscosity**

"A" side:	500 ± 200cps @ 77°F
"B" side:	500 ± 200 cps @ 77°F

■ **Liquid Material Density & Specific Gravity**

“A” side 9.19 lbs/gal (SG 1.103 g/ml)

Depending upon color.

“B” side (black) 8.41 lbs/gal (SG 1.010 g/ml)

■ **VOC's**

Contains no Volatile Organic Compounds.

■ **Toxicity**

ISO component contains polymeric Isocyanate requiring fresh air respirator, gloves, eye protection and protective clothing during application.

■ **Storage Stability or Shelf Life**

“A” side 6 months in unopened containers @ 50-90°F

“B” side 12 months in unopened containers @ 50-90°F.

■ **Reactivity**

- **Gel Time:** Gel in 5-8 seconds.
- **Tack Free:** Cure to handle in 30-40 seconds.
- **Recoat Time:** Recoatable for up to 8 hours.
- **Place-Into-Service Time:** Can be placed into light duty service in 8 hours. Chemical contact in 24 hours.
- **Cure Time:** Develops full chemical resistance and physical properties in 48 hours.

---

## Application

---

■ **Equipment**

VFI-200 requires hot airless plural component equipment capable of maintaining a minimum of 2000 psi and heat to 160°F. Higher pressures to 2500 psi may provide better mixing with enhanced physical properties for the end product. Contact Volatile Free, Inc. for specific spray gun recommendations.

■ **Material Preparation**

The product must be over 70° F for proper mixing and application.

■ **Mixing**

Proper mixing equipment must be used to mix the Poly (B) side. Mix for 20 minutes before using. Please contact VFI's technical department for specific mixer recommendations.

■ **Substrate Preparation**

All surfaces must be free of contaminants and be able to provide mechanical adhesion on a solid substrate. Steel should be white blasted per SSPC-SP10/NACE 2-3 mil. Sandblast or shotblast all concrete surfaces to achieve a profile equal to 80-100 grit sand paper. Refer to SP13/NACE 6.

■ **Primers**

Sealing porous surfaces with VFI-1007 is recommended. VFI-#11 Epoxy Primer is also recommended for cementitious and masonry surfaces where enhanced adhesion is needed.

VFI-1003 Primer is recommended for maximum adhesion to white blasted steel surfaces. Please contact Volatile Free, Inc. for more specific preparation recommendations.

■ **Clean-up Solvent**

Xylene, M.E.K. For reduced fire hazard use glycol ethers or environmentally acceptable chlorinated solvents.

■ **Limitations**

Contact VFI's Technical Department for appropriateness of this product for your specific application.

■ **Precautions**

See Safety Data Sheet for complete safety data. Protect from exposure to moisture. Water will cause the “A” component (ISO) to generate carbon dioxide with resulting high pressure in closed containers.

■ **Thinning**

Not Recommended

■ **Packaging**

5 gallon pails  
15 gallon ponies  
55 gallon drums  
270 gallon totes

For more information, contact us today at **800-307-9218**

Corporate Office: P.O. Box 344 • Brookfield, WI 53008 • (800) 307-9218 • (262) 787-0400 • Fax (262) 787-0500 • [www.volatilefree.com](http://www.volatilefree.com)

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc. As based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc. makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc. makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc. is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.