

VFI®-110 75 D INJECTABLE PLASTIC

VFI-110 75 D Injectable Plastic is a fast-setting, rigid urethane plastic with high strength and a quick demold time for increased part production. Its low viscosity allows it to be used in a reaction injection molding system with reduced air bubbles and waste. Depending on application needs, the plastic can produce a smooth, glossy or matte finish. When primed, it is fully paintable, and it cures tough to be machined or sanded. VFI-110's high amine content provides good temperature stability and chemical resistance to make repeatable castings for a variety of applications, including industrial part-making and prototyping.

- Superior Physical Properties Ideal for Industrial Part Making and Prototyping
- High Amine Content Offers Good Temperature Stability and Chemical Resistance
- Ultra-Easy 1A:1B Formulation Helps to Eliminate Costly Off-Ratio Mixes
- Room Temperature Cure Without the Need for Post Curing
- Fast Setting for Quicker Demold Times to Increase Part Production Rates
- Matching A and B Viscosities Allow for Easy and Consistent Injection
- Fully Cured Castings are Tough, Durable, and Easily Paintable

PHYSICAL PROPERTIES	TEST METHOD	TEST RESULTS
Shore Hardness	ASTM D2240	72 D
Tensile Strength	ASTM D638	4,000 psi
Tensile Modulus	ASTM D638	N/A
Elongation at Break	ASTM D638	75%
Flexural Modulus	ASTM D790	N/A
Izod Impact, Notched	ASTM D256	1.8 ft-lb/in
Linear Shrinkage	ASTM D2566	<0.010 in/in
Heat Deflection Temperature (@ 66 psi)	ASTM D648-18	N/A
Flame Test	UL 94-V0	No
Standard Cured Color	N/A	Neutral

LIQUID PROPERTIES	TEST METHOD	TEST RESULTS
Mix Ratio by Volume	N/A	1A:1B
Mix Ratio by Weight	N/A	100A:91.7B
Weight per Gallon A Side	ASTM D1475	9.66 lb/gal
Weight per Gallon B Side	ASTM D1475	9.08 lb/gal
Mixed Weight per Gallon	ASTM D1475	9.41 lb/gal
Viscosity A Side	ASTM D2196	600 cps
Viscosity B Side	ASTM D2196	1,000 cps
Mixed Viscosity	ASTM D2196	N/A
Pot Life	N/A	40 seconds
Gel Time	N/A	80 seconds
Demold Time	N/A	5 minutes
Full Cure Time	N/A	3 days

MANUFACTURER OF HIGH-PERFORMANCE POLYMERS
Toll-Free 800-307-9218 | www.volatilefree.com | info@volatilefree.com

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc., As based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.

VFI® -110 75 D INJECTABLE PLASTIC

THICKNESS REQUIREMENTS

VFI-110 does not have a thickness limit, but if the part you are injecting exceeds 5 pounds, a different material that has a longer working time should be used.

MOLD PREPARATION

The mold must be clean and free of oils, dirt, or debris. All surfaces in contact with VFI-110 must be properly sealed and coated with a release agent to prevent unwanted adhesion. Applying a release agent will also help prolong the life of the mold. Heating the mold between 70°F-150°F before injecting can accelerate the curing process. Compatible molds include urethane, metal, and platinum silicone when properly prepared.

MIXING

Before combining the A side (ISO) and B side (Poly) material, premix the B side material. The primary application method is to inject the material. A proportioner is required to inject the material into a mold. As a fast-setting material, VFI-110 does not need to be vacuum degassed.

POST-CURE

The casting can be demolded after 5 minutes if greater than 1/8 of an inch thick or 10 minutes if less than 1/8 of an inch. The material should be allowed to cure at room temperature for 16 hours. It does not require post-curing to achieve full properties. Full physical properties can be achieved in 3 days.

STORAGE/SHELF LIFE

Store between 60°F - 90°F in a clean, dry building. The shelf life of unopened containers is 12 months after the date of manufacture. Once open, use immediately, but if storing after opening, both sides must be nitrogen purged.

PRECAUTIONS

This product contains isocyanate, which may irritate the skin and is toxic if inhaled as particulate matter. Avoid prolonged breathing of vapors or repeated skin contact. Use only with adequate ventilation. Do not thin or add foreign material to the product. See Safety Data Sheet for complete safety instructions.