



ACRYLIC SYSTEM

The Acrylic System from VFI is a high-quality, easy-to-apply roof system for maintaining the life of roofs that are in good structural shape. Strong elastomeric properties of the acrylic coating help extend the roof's life for years with minimal maintenance required. It is a cost-effective alternative to silicone coatings when used on roofs with proper slope and drainage.

APPLICATION

- VFI-#11 9:1 Epoxy Primer is applied to promote adhesion of a coating to the roof substrate.
- VFI-630 Acrylic Flashing Grade should be used on seams and penetrations and to fill gaps of a 1/4 inch or less.
- VFI-640-1 Gray Acrylic Coating is applied as a base coat to build strength and film thickness.
- VFI-605-1 White Acrylic Coating is applied as a top coat to create a seamless, monolithic membrane, protecting the roof from moisture penetration and accelerated UV degradation for increased energy efficiency.

FOR USE OVER: Built-Up Roof (BUR), Concrete, EPDM, Metal, Modified Bitumen, Single-Ply, and Existing Acrylic Coatings.



FEATURES & BENEFITS

- **Improved Strength & Durability**
Strong elastomeric properties in both base and top coats help extend the roof's life.
- **Avoid Operation Shutdowns**
Roof coatings are less disruptive to business operations than costly roof replacements.
- **Field Proven & Tested Products**
Guaranteed quality from a trusted manufacturing company that has been a valued contributor to the roofing community for more than 25 years.



Cements and coatings for roofing systems as to an external fire exposure only 84GM

MANUFACTURER OF HIGH PERFORMANCE POLYMERS

Toll-Free 800-307-9218 | volatilefree.com | info@volatilefree.com

ACRYLIC SYSTEM



ACRYLIC SYSTEM

Tensile Strength	201 psi
Tear Strength	84 pli
Aged Solar Reflectance	0.76
Aged Thermal Emittance	0.92

HYBRID PREMIER SYSTEM

Tensile Strength	1,277 psi
Tear Strength	208 pli
Aged Solar Reflectance	0.70
Aged Thermal Emittance	0.90

SILICONE SYSTEM

Tensile Strength	426 psi
Tear Strength	29 pli
Aged Solar Reflectance	0.68
Aged Thermal Emittance	0.90

VFI-605-1 WHITE ACRYLIC COATING

PHYSICAL PROPERTIES

Tensile Strength	201 psi
Elongation	718%
Tear Strength	84 pli
Permeance	14 perms

LIQUID PROPERTIES

Solids by Volume	57%
Cure Time	2-4 hrs @ 75°F, 50% Rh
Recoat Window	2-48 hrs @ 75°F, 50% Rh
VOC	<25 g/L

VFI-640-1 GRAY ACRYLIC COATING

PHYSICAL PROPERTIES

Tensile Strength	201 psi
Elongation	718%
Tear Strength	84 pli
Permeance	14 perms

LIQUID PROPERTIES

Solids by Volume	57%
Cure Time	2-4 hrs @ 75°F, 50% Rh
Recoat Window	2-48 hrs @ 75°F, 50% Rh
VOC	<25 g/L

VFI-630 ACRYLIC FLASHING GRADE

PHYSICAL PROPERTIES

Tensile Strength	189 psi
Elongation	344%

LIQUID PROPERTIES

Solids by Volume	58%
Recoat Window	12 hrs min @ 75°F, 50% Rh
VOC	<25 g/L

VFI-#11 9:1 EPOXY PRIMER

LIQUID PROPERTIES

Solids by Volume	50.5%
Ratio by Volume (A:B)	9A:1B
Recoat Window	between 8 hrs - 7 days
VOC	35 g/L

Please reference individual technical data sheets or scan QR code for full product properties

MANUFACTURER OF HIGH PERFORMANCE POLYMERS

Toll-Free 800-307-9218 | volatilefree.com | info@volatilefree.com

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc., as based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc. makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc. makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc. is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.