



## HIGH-PRESSURE POLYUREA COATING

VFI polyurea coatings are fast-setting, two-component, and sprayable through high-pressure equipment. They can achieve high builds for the protection of surfaces in various industrial applications such as concrete, wood, metal, and other porous surfaces where you would encounter moisture. These surfaces typically need protection from chemicals, abrasion, and impact.



**VFI-200 50 D Slow Polyurea Coating** works best when spraying large horizontal surfaces or over geotextile fabric due to its slower setting speed of 15-20 seconds. It's also preferred for spraying areas that need little to no texture, as it does not self-texturize.



**VFI-201 50 D Polyurea Coating** is our general-purpose polyurea and is desired for its spraying capabilities as it hangs well on horizontal and vertical surfaces. With an unchanged, reliable formula, the coating is trusted for its adhesion and excellent properties.



**VFI-202 50 D Fast Polyurea Coating** is extremely fast at 6 seconds, which is why it's sprayed on vertical and overhead surfaces without the risk of dripping. Due to its setting time, it will also self-texturize. Unlike our other polyurea coatings, it must be sprayed in thin passes under 1/2-inch thick.

**Ideal applications:** secondary containment, mining, premier truck bedliner, sacrificial coatings, high-end packaging, boat docks, etc.

MANUFACTURER OF HIGH PERFORMANCE POLYMERS

Toll-Free 800-307-9218 | [volatilefree.com](http://volatilefree.com) | [info@volatilefree.com](mailto:info@volatilefree.com)

PHYSICAL PROPERTIES	TEST METHOD	JET FUEL	ETHANOL	GAS	DIESEL
<b>Chemical Immersion (One-Side Cell Test)</b> <b>Substrate: Concrete</b> <b>2 Specimens; exposure area of 2in Ø</b>		<b>ASTM D6943</b>			
Unexposed Control					
Blistering <sup>1</sup> [Rating]	ASTM D714 Size / Frequency	10			
Swelling / Thickness (mil)	ASTM D1005	-			
Surface Hardness <sup>2</sup> [pencil lead]	ASTM D3363 Scratch	H			
Indentation Hardness (Durometer) Type A-2	ASTM C661	90			
After 72h Exposure (no temp. gradient)					
Blistering <sup>1</sup> [Rating]	ASTM D714 Size / Frequency	10	10	10	10
Swelling / Thickness (mil)	ASTM D1005	54	54	88	3
Surface Hardness <sup>2</sup> [pencil lead]	ASTM D3363 Scratch	> 9H	> 9H	> 9H	H
Indentation Hardness (Durometer) Type A-2	ASTM C661	76	62	58	86
After 72h Exposure plus 48hr Recovery					
Blistering <sup>1</sup> [Rating]	ASTM D714 Size / Frequency	10	10	10	10
Swelling / Thickness (mil)	ASTM D1005	16	18	28	1
Surface Hardness <sup>2</sup> [pencil lead]	ASTM D3363 Scratch	4H	6H	7H	H
Indentation Hardness (Durometer) Type A-2	ASTM C661	86	76	78	88
<b>Chemical Immersion (Free Film Test)</b> <b>2 Specimens; ASTM D412 Die C</b>		<b>ASTM D543</b>			
Unexposed Control		ASTM D412			
Tensile Properties 5 Specimens; Die C Test @ 73.4 ± 3.6°F Test Rate = 20in / min ± 3%	Strength <sup>3</sup> (psi)	2137			
	Elongation (%)	310			
After 72h Exposure (no temp. gradient)		ASTM D412			
Tensile Properties 5 Specimens; Die C Test @ 73.4 ± 3.6°F Test Rate = 20in / min ± 3%	Strength <sup>3</sup> (psi)	755	321	362	2079
	Elongation (%)	130	90	85	278
After 72h Exposure plus 48hr Recovery		ASTM D412			
Tensile Properties 5 Specimens; Die C Test @ 73.4 ± 3.6°F Test Rate = 20in / min ± 3%	Strength <sup>3</sup> (psi)	2175	1228	1980	2376
	Elongation (%)	328	313	343	318

## MANUFACTURER OF HIGH PERFORMANCE POLYMERS

Toll-Free 800-307-9218 | [volatilefree.com](http://volatilefree.com) | [info@volatilefree.com](mailto:info@volatilefree.com)

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc. As based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.