

## VFI®-#11 9:1 EPOXY PRIMER

VFI-#11 9:1 Epoxy Primer is a two component, water-based, general use roof primer that adheres well to a variety of substrates. The primer is one part of a full commercial roof restoration system and acts as an adhesion promoter for silicone, acrylic, or urethane roof coatings. Applying VFI's industry leading epoxy primer is important for increasing the bond of liquid applied roof coatings to any substrate and helps to protect your project from future failures.

- Among the most trusted epoxy primers on the market
- Easily combine and mix material without the need for measuring or an additional bucket
- Penetrates and seals surfaces to enhance the bonding of top coats to almost any substrate
- Distinct color to detect where coverage is needed while priming or during top coat application
- Non-toxic with a VOC-compliant content that exceeds EPA standards

LIQUID PROPERTIES	TEST METHOD	TEST RESULTS
Solids by Weight	ASTM D1644	59%
Solids by Volume	ASTM D2697	50.5%
Liquid Density A Side	ASTM D1475	12.27 lbs/gal
Liquid Density B Side	ASTM D1475	7.86 lbs/gal
Mixed Liquid Density	N/A	11.83 lbs/gal
Specific Gravity A Side	N/A	1.473 g/mL
Specific Gravity B Side	N/A	0.945 g/mL
Mixed Specific Gravity	N/A	1.42 g/mL
Ratio by Volume (A:B)	N/A	9A:1B
Ratio by Weight (A:B)	N/A	14A:1B
Recoat Window	N/A	between 8 hrs - 7 days
Full Cure	N/A	7 days
VOC	N/A	35 g/L



Cements and coatings for roofing systems as to an external fire exposure only 84GM

**MANUFACTURER OF HIGH PERFORMANCE POLYMERS**

Toll-Free 800-307-9218 | [volatilefree.com](http://volatilefree.com) | [info@volatilefree.com](mailto:info@volatilefree.com)

# VFI®-#11 9:1 EPOXY PRIMER

## EQUIPMENT

The primer can be applied to the substrate with airless spray equipment, industrial paint brushes, or nap rollers. For smaller projects (under 10,000 sq ft) when spraying, an airless spray pump like Graco Ultra 395 PC is recommended as it can provide a needed pressure between 1,500-2,000 psi. It has a maximum flow rate of .54 GPM with ¼ inch hoses up to 150 ft. For larger projects (over 10,000 sq ft), we recommend using Graco UltraMax Sprayers capable of up to 1.10 gpm and 3,300 psi of constant pressure with hoses up to 300 ft. Graco Airless Guns that are suitable to the pump psi outputs with .021 tips are also recommended.

## SURFACE PREPARATION

The surface should be clean, dry, and free of oils, dirt, or films that may prevent adhesion. Power wash as needed. Repair or replace any damaged areas on the roof, including drains, vents, flashing, seams, etc. Areas with mildew, fungus, or algae can be treated with a concentrated chlorine solution. Use VFI-1009 Cleaning Detergent to scrub areas with grease, oil, or animal fats. Rinse cleaning agents off the roof and allow the surface to dry before priming.

## MIXING

The A side (Iso) should be premixed before combining with the B side (Poly). Mix the material until uniform before use. Mix times may vary based on volume and mixing method.

## APPLICATION REQUIREMENTS

The material can be applied between 50°F - 120°F, but the temperature must remain above 50°F until cured. Rain or moisture cannot be present during application. Stop application a minimum of two hours before rain or when the relative humidity is reached. Bring the material temperature to a minimum of 65°F before use.

Apply the primer at a minimum of .25 gallons per square. Check specifications for required wet and dry film thickness. Allow the primer to cure for a minimum of 8 hours before topcoat application. Cure time may vary depending on temperature and humidity. If recoat is needed, it should be applied the next day or within 48 hours.

## CLEANING

Clean all tools and equipment, including brushes, rollers, spray guns, and spray lines with water. If the material has cured on equipment, use chemically dry mineral spirits or a similar cleaning solvent.

## STORAGE/SHELF LIFE

The material shelf life is 12 months from the date of manufacture. Store in a dry, temperature-controlled space in sealed and unopened containers between 60°F - 90°F. As a water-based product, it should be protected from freezing.

## PRECAUTIONS

VFI-#11 is not UV color stable and has no long-term UV testing. Protect the material from freezing. Avoid breathing in vapors or repeated skin contact. Do not thin or add foreign material to the product. See Safety Data Sheet for complete safety data.