



## VFI®-5216 16 PCF Flexible Polyurethane Foam

**VFI®-5216 16 PCF Flexible Polyurethane Foam** is a 16lb per cubic foot, flexible pour foam that is compressible while also having good bounce back. VFI-5216 is a two part, two to one by volume foam that works in any machine injected system while also having a slow enough gel time to allow hand pouring. VFI-5216 Flexible Polyurethane Foam is self-skinning which enables it to create a nice foam skin from a metal mold for increased finished appearance. With a slow cream time for additional mixing and pouring, VFI-5216 offers options to create a high density flexible part.

### → Technical Usage

VFI®-5216 16 PCF Flexible Polyurethane Foam has been used in the following applications and may be used in many more applications. Contact Volatile Free, Inc. for more information on any specific applications.

- Cast Stone
- Manufactured Stone
- Molding and Casting
- Precast

### → Color

Standard color available is white. For additional premium colors or color matching services contact Volatile Free, Inc.

### → UV Stability

This product is **NOT** UV color stable and has no long-term UV testing. For additional information contact Volatile Free, Inc.

### → Coverage/Thickness Requirement

Contact Volatile Free, Inc. for thickness requirements and specifications.

### → Storage Stability/Shelf Life

12 month shelf life from date of manufacture when stored and sealed in unopened containers between 40°F - 75°F. Opened containers may be resealed with a nitrogen purge, but shelf life will be significantly shortened. Material should be brought to a minimum temperature of 65°F before use.

### → Equipment

For instructions and equipment requirements, contact Volatile Free, Inc.

### → Surface Preparation

All surfaces should be cleaned, prepped and free of any oils, dirt or debris. To demold, material must be non-porous or sealed with a chemical sealant. A release agent should be used on all products intended to be demolded. Contact Volatile Free, Inc. with any additional questions.

### → Mixing

Pre-mixing Poly (B) components until uniform is required before combining Poly (B) and Iso (A). If pouring material by hand pre-weighed Poly (B) must be poured into pre-weighed Iso (A) and then mixed until uniform and transferred to a new container to mix until uniform again before use. Product must be fully mixed and used before the duration of the cream time (initial rise). Mix times may vary depending on volume and mixing method. Please contact Volatile Free, Inc. for more information on any specific mixing questions and requirements.

### → Material Application

Temperature should be between 50°F - 100°F when the product is being used. The pot life will shorten with any increases in temperature beyond 72°F. Ensure surfaces in contact with the material are properly sealed and released before mixing to prevent any unwanted adhesion. Contact Volatile Free, Inc. for more information on recommended release agents or sealants.

### → Primers

Contact Volatile Free, Inc. on any primer questions.

### → Cleanup Solvent

Preferred cleanup solvent is xylene or MEK. Please contact Volatile Free, Inc. for more information on cleanup of equipment and tools.

### → Thinning

Do not thin prior to application.

### → Precautions

Contains isocyanate that may be irritating to the skin and is toxic if inhaled as particulate matter. See Safety Data Sheet for complete safety data. Do not add any foreign material to this product. Avoid prolonged breathing of vapors and prolonged or repeated skin contact. Use only with adequate ventilation.

# VFI®-5216 16 PCF FLEXIBLE POLYURETHANE FOAM

## Application Method

SPRAY	QWIK SPRAY	BRUSH	TROWEL	ROLLER	INJECTABLE	POUR
-	-	-	-	-	X	X

## Physical Properties

Solid Material Density	16 PCF
Free Rise Density	16 PCF

## Liquid Properties

Solids by Weight	100%
Solids by Volume	100%
Liquid Density A Side	10.03 lbs/gal
Liquid Density B Side	8.57 lbs/gal
Ratio by Volume (A:B)	1A:2B
Ratio by Weight (A:B)	100A:170.93B
Viscosity A Side	500 cps
Viscosity B Side	1500 cps
Compression at 10%	11.29 pcf
Compression at 13%	13.02 pcf
Max Load	13.87 pcf
Cream Time	30 seconds
Gel Time	140 seconds
Rise Time	140 seconds

## Packaging



TOTE DRUM 5 GALLON 1 GALLON

**VOLATILE FREE, INC.**

19500 JANACEK COURT | BROOKFIELD, WI 53045 | (262) 787-0400 | TOLL-FREE (800) 307-9218 | FAX (262) 787-0500 | INFO@VOLATILEFREE.COM

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc., as based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc. makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc. makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc. is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.