

VFI®-4580 82 D UV STABLE CLEAR POLYURETHANE

VFI-4580 82 D UV Stable Clear Polyurethane is a two-component liquid urethane plastic that offers ample time to cast parts that are water-clear with no distortion. The cured plastic is highly rigid and durable, making castings tough and impact-resistant. The plastic is UV color-stable for use in indoor or outdoor environments. VFI-4580 is best used for applications that require transparency, such as prototype models, decorative pieces, and industrial parts. When casting large parts, VFI recommends using our 50-minute (VFI-4581) or 205-minute (VFI-4582) formulas.

- Crystal clear castings perfect for prototyping applications
- High heat deflection temperature at 145°F (62.8°C)
- Long working time provides sufficient time to mix, degas, and pour by hand
- Can be vacuum degassed for bubble-free castings

PHYSICAL PROPERTIES	TEST METHOD	TEST RESULTS
Shore Hardness	ASTM D2240	82 D
Tensile Strength	ASTM D638	8,500 psi
Tensile Modulus	ASTM D638	340,000 psi
Elongation at Break	ASTM D638	35%
Flexural Modulus	ASTM D790	386,000 psi
Izod Impact, Notched	ASTM D256	1.06 ft-lb/in
Linear Shrinkage	ASTM D2566	<0.005 in/in
Heat Deflection Temperature (@ 66 psi)	ASTM D648-18	145°F ± 2°F
Flame Test	UL 94-V0	No
Standard Cured Color	N/A	Transparent

LIQUID PROPERTIES	TEST METHOD	TEST RESULTS
Mix Ratio by Volume	N/A	116.65A:100B
Mix Ratio by Weight	N/A	120A:100B
Weight per Gallon A Side	ASTM D1475	8.91 lb/gal
Weight per Gallon B Side	ASTM D1475	8.66 lb/gal
Mixed Weight per Gallon	ASTM D1475	8.83 lb/gal
Viscosity A Side	ASTM D2196	550 cps
Viscosity B Side	ASTM D2196	600 cps
Mixed Viscosity	ASTM D2196	600 cps
Pot Life	N/A	10 minutes
Gel Time	N/A	15 minutes
Demold Time	N/A	4 hours
Full Cure Time	N/A	N/A

MANUFACTURER OF HIGH-PERFORMANCE POLYMERS
Toll-Free 800-307-9218 | www.volatilefree.com | info@volatilefree.com

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc., As based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.

VFI®-4580 82 D UV STABLE CLEAR POLYURETHANE

THICKNESS REQUIREMENTS

We recommend pouring at a thickness of 1/16 of an inch to ½ an inch to create the necessary film to demold the part and prevent shrinking at corners or bubbles from forming. Pour the material into a single spot at the lowest point of the mold and allow it to seek its level. A consistent pour will minimize air bubbles.

MOLD PREPARATION

All surfaces should be clean, dry, and free of dirt, dust, and debris. Porous surfaces should be properly sealed before casting. Spraying a release agent is recommended to extend the life of the mold and prevent unwanted adhesion. When working with prototyping urethane molds, release is required. VFI recommends using Chem-Trend's MR-515 Aerosol or a similar release agent. Be careful not to overspray the release, as this may result in a shiny/glossy surface or loss of detail transferred to the casting.

For smaller molds, we recommend heating the mold up to 150°F for 4 hours before casting. Heated molds can help to reduce bubbles and demold times. Compatible molds include urethane rubber, aluminum, and platinum silicone. A platinum silicone mold is the preferred molding type to allow for the full transfer of detail, but post-curing VFI-4580 is required when using a silicone mold.

MIXING

The material should be used at room temperature for proper mixing and application. Premix the B side (Poly) material before each use. Avoid introducing extra moisture or air into the mix. The A side (Iso) does not need to be premixed.

VFI recommends vacuum degassing the material for bubble-free castings. Prepare a container that is an appropriate size for degassing with at least 2/3 of headspace. Measure the A side material and pour it into the mixing container. Then, measure the B side material and pour it into the same container. Slowly hand-mix the material until uniform. Make sure to scrape the sides and bottom of the container. To avoid an uneven mix, pour the material into a different, clean container and mix again. VFI-4580 provides ample time to mix, degas, and pour before the end of the 10-minute pot life.

POST-CURE

Castings should be kept in the mold until fully cured to prevent warping. Demold time is dependent on the volume of material used and pour thickness. Thin-walled parts may not cure as well without heat. VFI-4580 should sit for at least 4 hours at room temperature before demolding. Post-curing the material in an oven for 8 hours at 170°F is required to achieve full physical properties.

STORAGE/SHELF LIFE

Store in a clean, dry place between 60°F - 90°F. The shelf life of unopened containers is 12 months from the date of manufacture. To extend the shelf life of opened containers, you must keep the containers sealed and nitrogen purge both sides of the material.

PRECAUTIONS

VFI-4580 contains isocyanate, which may be irritating to the skin and is toxic if inhaled as particulate matter. Avoid prolonged breathing of vapors and repeated skin contact. Use only with adequate ventilation. The material is moisture sensitive and may foam if exposed to too much moisture. Do not add foreign material to the product. See Safety Data Sheet for complete safety information.